



**SPECIALTY POLYMERS, INC.**

Leaders in Innovative Polymer Technology

## Products Summary Guide Textile Products

Product	Type	Weight solids, %	pH	Density (lbs/gal)	Tg (°C)	Visc. cps	Particle size, microns	Self crosslinking	Remarks
<b>BACK COATINGS</b>									
RayCryl 1853	A	55	4.0	8.78	-26	550	0.25	yes	Very soft, flexible film with excellent durability; good UV resistance
RayCryl 1856	A	55	4.0	8.78	36	550	0.25	yes	Very firm film with excellent durability; good UV resistance
RayCryl 1859	A	55	4.0	8.78	7	550	0.25	yes	Medium flexibility with excellent durability; good UV resistance
RayCryl 1809	A	59	4.2	8.60	14	550	0.25	yes	Medium flexibility with excellent durability; good UV resistance and non-yellowing
<b>SCREEN PRINT AND PAD BINDERS</b>									
RayCryl 1850	A	45	4.5	8.60	-11	260	0.20	yes	Excellent UV resistance; non-yellowing
<b>FABRIC HAND BUILDER</b>									
RayVace 1724	V/A	45	4.5	8.90	36	125	0.25	yes	Excellent balance of value and performance

A = Acrylic; V/A = Vinyl Acrylic



**West Coast:**  
P.O. Box 299  
2475 Progress Way  
Woodburn, OR 97071  
(800) 770-7523

**East Coast:**  
869 Old Richburg Road  
Chester, SC 26706  
(800) 671-2842

02.16.10

1-800-770-7523

www.specpoly.com

info@specpoly.com

